

Listing of Claims

1. (Previously presented) A method of manufacturing a gate electrode of improved channel effect and improved gate oxide reliability, comprising:
providing a substrate with a patterned and etched layer of gate oxide over the surface thereof and a patterned and etched layer of gate material over said patterned gate oxide, a LDD impurity implant into the substrate having been performed and annealed self-aligned with the patterned and etched layer of gate material;
performing a plasma treatment of the patterned and etched layer of gate material and exposed surfaces of the provided substrate; and
creating spacers over sidewalls of the patterned and etched layer of gate material.
2. (Currently amended) The method of claim 1, the plasma exposure being a H₂ based plasma exposure.
3. (Currently amended) The method of claim 1, the plasma exposure being an O₂ based plasma exposure.
4. (Original) The method of claim 1, the plasma exposure being a N₂ based plasma exposure.
5. (Original) The method of claim 1, additionally pocket implants having been performed into the substrate after the LDD impurity implant have been performed.
6. (Original) The method of claim 1, additionally completing the gate electrode and conductive interconnects there-to after creating spacers over sidewalls of the patterned and etched layer of gate material.

7. (Original) A method of manufacturing a gate electrode of improved channel effect and improved gate oxide reliability, comprising:
- providing a substrate, an active surface having been bounded over the substrate by creating regions of field isolation;
 - creating a layer of gate oxide over the active surface;
 - creating a layer of gate material over the gate oxide;
 - patterning and etching the layer of gate material and layer of the gate oxide, creating a gate electrode having sidewalls over the active surface, exposing the substrate;
 - performing an impurity implant into the exposed substrate, self-aligned with the gate electrode;
 - performing a plasma treatment of the sidewalls of the gate electrode and the exposed substrate;
 - creating spacers over the sidewalls of the gate electrode; and
 - completing the gate electrode, including conductive interconnects there-to.
8. (Original) The method of claim 7, the plasma treatment being a H₂ based plasma exposure.
9. (Currently amended) The method of claim 7, the plasma treatment being an O₂ based plasma exposure.
10. (Original) The method of claim 7, the plasma treatment being a N₂ based plasma exposure.
11. (Original) The method of claim 7, the impurity implant comprising LDD implants.

12. (Original) The method of claim 7, the impurity implant comprising LDD implants followed by pocket implants.
13. (Original) The method of claim 7, the impurity implant being followed by an anneal.
14. (Currently amended) A method of manufacturing a gate electrode of improved channel effect and improved gate oxide reliability, comprising:
providing a substrate, an active surface having been bounded over the substrate by creating regions of field isolation;
creating a layer of gate oxide over the active surface;
creating a layer of gate material over the gate oxide;
patterning and etching the layer of gate material and layer of the gate oxide;
creating a gate electrode having sidewalls over the active surface, exposing the substrate;
performing impurity implants into the exposed substrate, self-aligned with the gate electrode;
performing a $[[\text{Hz}]]$ H_2 based plasma treatment of the sidewalls of the gate electrode and the exposed substrate;
creating spacers over the sidewalls of the gate electrode; and
completing the gate electrode, including conductive interconnects there-to.
15. (Original) The method of claim 14, the impurity implants comprising LDD implants.
16. (Original) The method of claim 14, the impurity implants comprising LDD implants followed by pocket implants.

17. (Original) The method of claim 14, the impurity implants being followed by an anneal.
18. (Original) A method of manufacturing a gate electrode of improved channel effect and improved gate oxide reliability, comprising:
providing a substrate, an active surface having been bounded over the substrate by creating regions of field isolation;
creating a layer of gate oxide over the active surface;
creating a layer of gate material over the gate oxide;
patterning and etching the layer of gate material and layer of the gate oxide, creating a gate electrode having sidewalls over the active surface, exposing the substrate;
performing impurity implants into the exposed substrate, self-aligned with the gate electrode;
performing an O₂ based plasma treatment of the sidewalls of the gate electrode and the exposed substrate;
creating spacers over the sidewalls of the gate electrode; and
completing the gate electrode, including conductive interconnects there-to.
19. (Original) The method of claim 18, the impurity implants comprising LDD implants.
20. (Original) The method of claim 18, the impurity implants comprising LDD implants followed by pocket implants.

21. (Original) The method of claim 18, the impurity implants being followed by an anneal.

22. (Original) A method of manufacturing a gate electrode of improved channel effect and improved gate oxide reliability, comprising:

- providing a substrate, an active surface having been bounded over the substrate by creating regions of field isolation;

- creating a layer of gate oxide over the active surface;

- creating a layer of gate material over the gate oxide;

- patterning and etching the layer of gate material and layer of the gate oxide, creating a gate electrode having sidewalls over the active surface, exposing the substrate;

- performing impurity implants into the exposed substrate, self-aligned with the gate electrode;

- performing a N₂ based plasma treatment of the sidewalls of the gate electrode and the exposed substrate;

- creating spacers over the sidewalls of the gate electrode; and

- completing the gate electrode, including conductive interconnects there-to.

23. (Original) The method of claim 22, the impurity implants comprising LDD implants.

24. (Original) The method of claim 22, the impurity implants comprising LDD implants followed by pocket implants.

25. (Original) The method of claim 22, the impurity implants being followed by an anneal.

26. (Currently amended) A method of manufacturing a gate electrode of improved channel effect and improved gate oxide reliability, comprising:

- providing a substrate, an active surface having been bounded over the substrate by creating regions of field isolation;
- creating a layer of gate oxide over the active surface;
- creating a layer of gate material over the gate oxide;
- patterning and etching the layer of gate material and layer of the gate oxide, creating a gate electrode having sidewalls over the active surface, exposing the substrate;
- performing a LDD impurity implant into the exposed substrate, self-aligned with the gate electrode;
- performing a pocket impurity implant into the exposed substrate, self-aligned with the gate electrode;
- performing an anneal of the LDD and pocket impurity implants;
- performing a H₂-based or an N₂ based or an [[O₂]] O₂ based plasma treatment of the sidewalls of the gate electrode and the exposed substrate;
- creating spacers over the sidewalls of the gate electrode; and
- completing the gate electrode, including conductive interconnects there-to.

27. (Previously presented) A method of manufacturing a gate electrode, comprising:

- providing a substrate;
- forming a patterned gate oxide over said substrate;
- forming a patterned gate material over said patterned gate oxide;
- forming a pair of LDD structures in said substrate and respectively adjacent to said patterned gate oxide;
- performing a plasma treatment to said patterned gate material and said

substrate; and

respectively forming a pair of spacers over sidewalls of said patterned gate oxide and gate material following the plasma treatment.

28. (Original) The method of claim 27, the plasma treatment being a H₂ based plasma treatment.

29. (Currently amended) The method of claim 27, the plasma treatment being an [[02]] O₂ based plasma treatment.

30. (Original) The method of claim 27, the plasma treatment being a N₂ based plasma treatment.

31. (Original) The method of claim 27, the forming a pair of LDD structures being followed by an anneal.

32. (Previously presented) A method of manufacturing a gate electrode, comprising the sequential steps of:

providing a substrate;

forming a patterned gate oxide over said substrate;

forming a patterned gate material over said patterned gate oxide;

forming a pair of LDD structures in said substrate and respectively adjacent to said patterned gate oxide;

performing a plasma treatment to said patterned gate material and said substrate; and

respectively forming a pair of spacers over sidewalls of said patterned gate oxide and gate material.